

Q.P KRAFT

Gypsum powder filler (copolymer powder of vinyl acetate and ethylene), using as jointing filler and skim coat for interior gypsum board.

It meets European standard EN 998-1.

Special Features:

1. Elastic properties.
2. Filling properties.
3. Acrylic, excellent adhesion.
4. Odorless, mercury-free and lead-free.
5. Environmentally friendly, non-toxic and non-flammable

Mixing:

1. Put clean water (without chemical additives) in a clean mixing container.
2. Mix at a ratio of 3-4 kg of powder to 1 liter of water.
3. Stir the admixture by a hand for 30 seconds.
4. Make sure that everything is mixed .
5. Use an electrical agitator to mix the admixture for one minute.

Application:

1. Fill a layer of QP Kraft in the joint using a trowel and wait to dry.
2. Use fiberglass tape to cover joints.
3. Apply second coat of QP Kraft to penetrate into the joint
4. Scrape the surface well
5. Apply a coat of primary emulsion.
6. Apply two layers of silky coat putty to make surface smooth.
7. Apply two layers of emulsion for final finishing.

Notes:

- Do not mix with cement.
- Use admixture through 30 minutes after mixing.
- It is advised not to apply if below 7 °c.

Package & Storage:

- 20 kg paper bags .
- Stored away from direct heat or frost unopened ,in a dry location ,for a maximum of 12 months from the date of production.

Technical Data:

Physical State	Powder
Binder	Copolymer powder of vinyl acetate and ethylene
Filler	Fine graded fillers, gypsum
Specific density	1.7
Layer thickness	3-5 mm
Consumption	2m ² /kg (thickness 3 mm)
Safety	Nontoxic and fire resistant.

European standard EN 998-1

STANDARD			
LIMIT OF STANDARD	Compressive Strength ≥ 0.4 N/mm ²	Adhesive Strength ≥ 0.3N/mm ²	Capillary Water Absorption ≤ 0.4 kg/m ²
Q.P Kraft	≥ 0.4 N/mm ²	≥ 0.3 N/mm ²	≤ 0.4 kg/m ²